

### Reolube<sup>®</sup> Turbofluid 46B Fire Resistant Hydraulic Fluid

#### DESCRIPTION

**Reolube<sup>®</sup> Turbofluid 46B** is a high performance, fire-resistant hydraulic fluid designed for use in electrohydraulic governor control systems of steam turbines, including systems using fine tolerance servo valves. It is a triaryl phosphate based on synthetic butylated phenol and is formulated to provide good oxidation stability. Physical properties such as air release, foaming and demulsibility are also carefully controlled within turbine manufacturers' specified limits.

**Reolube<sup>®</sup> Turbofluid 46B** is also recommended for use as a fire-resistant lubricant, for example in steam and gas turbines. **Reolube<sup>®</sup> Turbofluid 46B** is approved by major OEMs such as General Electric, Siemens, Mitsubishi Hitachi Power Systems and Alstom and is approved by FM Global against Standard 6930 for 'Less flammable hydraulic fluids'. It also meets the requirements of ISO Standard 12922 and ASTM D4293 for HFDR-type fire-resistant hydraulic fluids.

**Reolube<sup>®</sup> Turbofluid 46B** is fully compatible with other phosphate ester EHC fluids.  
The values given in the tables are typical and do not constitute specification limits.

#### Technical data\*



### Reolube<sup>®</sup> Turbofluid 46B Fire Resistant Hydraulic Fluid

PHYSICAL PROPERTY	UNIT	TYPICAL VALUE	TEST METHOD
Color	Hazen	1	ASTM D1500
Kinematic Viscosity at 100°C	SUS (cSt)	25.019 (5.4)	ISO 3104/ ASTM D445
Kinematic Viscosity at 40°C	SUS (cSt)	206.12 (44.5)	ISO 3104/ ASTM D445
Specific Gravity at 20°C		1.15	ISO 3675/ ASTM D4052
Pour Point	°F (°C)	-11.2 (-24)	ISO 3016
Acid Number	mgKOH/g	0.05	ISO 6619/ ASTM D664
Chlorine Content	ppm	6	Microcoulometric
Water Content	%w/w	0.04	ISO ISO 760
Volume Resistivity at 20°C	MOhm.m	200	IEC 60247
Particulate Contamination		Passes -/15/12	ISO 4406
Foaming Tendency at 75.2°F (24°C)	ml	10	ISO 6247/ ASTM D892
Foaming Stability at 75.2 F (24°C)	ml	0	ISO 6247/ ASTM D892
Air Release at 122°F (50°C)	min	4.0	ISO 9120/ ASTM 3427
Water Separation (Demulsification)	min	5	ISO 6614/ASTM D1401

*\*The analytical data are guide values.*



**Reolube<sup>®</sup> Turbofluid 46B**  
Fire Resistant Hydraulic Fluid

FIRE RESISTANCE PROPERTY	UNIT	TYPICAL VALUE	TEST METHOD
Flash Point (open cup)	°F (°C)	503.6 (262)	ASTM D92
Fire Point (open cup)	°F (°C)	669.2 (354)	ASTM D92
Autoignition Temperature (method A)	°F (°C)	1004 (540)	DIN 51794
Autoignition Temperature (method B)	°F (°C)	993.2 (534)	ASTM E659
Wick Ignition Maximum Persistence	s	0.7	ISO 14935
Spray Ignition Maximum Persistence of Burning	s	8	ISO 15029-1
Spray Ignition Stabilised ignitability grade		E	ISO 15029-2
Spray Ignition Stabilised flame length grade		D	ISO 15029-2
Hot Manifold Ignition	°F (°C)	No flashing or burning on tube at 1338.8 (726) (pass)	ISO 20823

*\*The analytical data are guide values.*

LUBRICATION PERFORMANCE	UNIT	TYPICAL VALUE	TEST METHOD
Vickers Vane Pump Test ring weight loss	mg	11.6	ISO 20763
Vickers Vane Pump Test ring vane weight loss	mg	4.9	ISO 20763
Vickers Vane Pump Test ring total weight loss	mg	16.5	ISO 20763
Four Ball Wear Test wear scar diameter	mm	0.52	ASTM D4172
FZG Gear Test Failure Load Stage		8	DIN 51354 part 1
FZG Gear Test Specific Weight Loss	mg/kWh	0.46	DIN 51354 part 1

*\*The analytical data are guide values.*



### Reolube<sup>®</sup> Turbofluid 46B Fire Resistant Hydraulic Fluid

STABILITY PROPERTY	UNIT	TYPICAL VALUE	TEST METHOD
Oxidative Stability Method A acid value change	mgKOH/g	0.05	DIN EN 14832
Oxidative Stability Method A Metal weight changes iron, copper	mg	-0.1, -0.1	DIN EN 14832
Oxidative Stability Method B viscosity change at 40°C	%	1.5	FTM 791 5308.7
Oxidative Stability Method B acid value change	mgKOH/g	0.05	FTM 791 5308.7
Oxidative Stability Method C time to 275 kPa pressure drop	min	216	ASTM D2272
Hydrolytic Stability Method A acid value change in fluid	mgKOH/g	0.27	DIN EN 14833
Hydrolytic Stability Method A acid value change in water	mgKOH/g	0.46	DIN EN 14833
Hydrolytic Stability Method B acid value change in fluid	mgKOH/g	0.13	ASTM D2619
Hydrolytic Stability Method B acid value change in water	mgKOH/g	0.17	ASTM D2619
Hydrolytic Stability Method B copper weight change	mg	0.04	ASTM D2619

*\*The analytical data are guide values.*



**Reolube<sup>®</sup> Turbofluid 46B**  
Fire Resistant Hydraulic Fluid



### Reolube® Turbofluid 46B

Fire Resistant Hydraulic Fluid

MATERIAL APPLICATION	SEALS PACKING HOSES ACCUMULAT- ORS	WIRES AND CABLE INSULATION	PAINTS	FILTERS
Acrylic			U	
Activated Alumina				A
Alkyd Paint			A	
Butyl Rubber	R			
Cellulose				A
Ethylene-Propylene Rubber	R			
Epoxy Paint (cured)			R	
Fuller's Earth				A
Ion Exchange Resins				R
Natural Rubber	U			
Neoprene	U			
Nitrocullulose			U	
Nitrile Rubber	U			
Nylon	R	R		
Paper				A
Phenolic Resins			U	
Polyethylene		A		
Polypropylene		A		
Polyurethane Paint			A	
PVC		U		
Silicone Rubber	U	A		
Teflon	R	R		
Vinyl Ester Paint			A	
Viton Rubber	R			



### Reolube<sup>®</sup> Turbofluid 46B Fire Resistant Hydraulic Fluid

*\*The analytical data are guide values.*

#### Packaging

Reolube<sup>®</sup> Turbofluid 46B is available in 230kg drums.

#### Storage conditions

Store in a cool dry location

#### Handling

In accordance with safe industrial practice, gloves, safety glasses and an apron should be worn when handling Reolube<sup>®</sup> Turbofluids, and spillages should be dealt with immediately. If allowed to overheat, breathing the fumes should be avoided.

For more extensive information on the safe handling and use of this product, see the Safety Data Sheet.

This information and our technical advice – whether verbal, in writing or by way of trials – is subject to change without notice and given in good faith but without warranty or guarantee, express or implied, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided - especially that contained in our safety data and technical information sheets - and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

©2019 LANXESS and the LANXESS Logo are trademarks of LANXESS Deutschland GmbH or its affiliates. All trademarks are registered in many countries in the world.

North America  
+1.833.LANXESS  
customer.care@lanxess.com

Europe, Middle East & Africa  
+44.161.875.3800  
emea.export@lanxess.com

South & Central America  
+55.19.3522.5083  
atendimento.cliente@lanxess.com

Asia Pacific  
+86.21.6109.6666  
Orders.apac@lanxess.com

